

# Hydroproof Xtra

## Single component acrylic polymer for cement based waterproof composite coating membrane

### Uses

Provides an effective and economical method of waterproofing to concrete and masonry surfaces, by mixing with cement and application by brush.

### Advantages

- Non - toxic, non-flammable and user friendly
- Provides a tough, impermeable waterproof membrane
- Can be applied by brush, on horizontal and vertical surfaces
- Excellent adhesion to concrete and masonry surfaces
- Protects concrete and mortar from natural elements such as wind, rain, sunlight
- Breathable - allows inside water vapour to escape

### Description

Hydroproof Xtra is formulated to be mixed with cement on site or simply brush applied over concrete or masonry surfaces to provide an effective waterproof membrane.

### Technical support

Fosroc provides a technical advisory service supported by a team of specialists in the field.

### Areas of application

Below sloping screed or waterproof plaster on :

- Roofs, terraces and balconies as a sandwich layer
- Pools and fountains
- Reservoirs and channels
- End walls subjected to rain

### Properties

Water absorption	: 1% maximum
Pot life at 30°C	: 30 min.
Application temperature	: Not less than 10°C
Toxicity	: Non-toxic
Bond strength to concrete	: Approx. 1 N/mm <sup>2</sup>

Note: The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary, dependent on actual site conditions

## Application instructions

### Preparation

All surfaces to be treated with Hydroproof Xtra must be thoroughly cleaned by a wire brush or other mechanical means, to remove all dust, laitence or debris. The surface must also be free from oil, grease, wax or any other form of foreign matter which might affect adhesion. Spalled and deeply disintegrated concrete or mortar must be removed to a sound substrate and repaired suitably before coating.

### Priming

Before application, the surface should be primed with Hydroproof Xtra as follows:

1 part of Hydroproof Xtra : 2 parts of Water : 4 parts of Cement

Mixed material with the above proportion will cover an area of 16-17m<sup>2</sup> for 1L of Hydroproof Xtra.

### Topcoat

Hydroproof Xtra acrylic polymer shall be mixed with neat cement in the ratio of 1:2 respectively, to obtain a uniform and consistent slurry avoiding any lump formation. This can be achieved with a low duty, low speed drilling machine attached with a mixing paddle. Do not mix for more than 2 minutes. Do not mix more material than which can be used within the pot life. Retempering the mix with water should not be done. Occasionally stir the material till the entire quantity is applied, so that solids do not settle at the bottom of the container.

### Mixing Ratio

Hydroproof Xtra liquid	Neat cement
0.5L	1 kg
1L	2kg
5L	10 kg
20L	40 kg
200L	400 kgs

For white colour - mix white cement, for other colours, add cement compatible pigments to white cement.

### Application

For best results, wet the surface before coating. Apply the mix with a short, stiff bristle brush like a paint to an approximate thickness of 1 to 2mm. During the first 12 hours of curing, Hydroproof Xtra surface must be protected from abrasion, rain or other adverse conditions. No traffic shall be allowed within 48 hours after application.

# Hydroproof Xtra

---

Normally 2 coats of application of Hydroproof Xtra are recommended. First coat should be allowed to air dry for 5 - 6 hours. After application of the final coat, initial air drying shall be allowed for 2 to 6 hours. During this period water should not be used for curing. Moist curing should be done for the next 24 hours by spraying water on Hydroproof Xtra coating. Following moist curing, Hydroproof Xtra should be allowed to dry for three days before subjecting it to submersion in water.

## Estimating

## Packaging

Available in 0.5, 1, 5 & 20 & 200 L packs.

## Coverage

**Priming coat** - 16-17m<sup>2</sup> / L.

**Topcoat** - 4.5 - 5.0m<sup>2</sup> / L / coat.

However the practical consumption varies depending on the texture and porosity of the surface and the application thickness.

## Storage

Hydroproof Xtra liquid has a shelf life of 12 months, when stored in unopened containers under normal warehouse conditions.

## Precautions

### Health & Safety

Hydroproof Xtra is water based and non-toxic. Gloves should be worn during application. Any splashes on the skin or eyes must be washed off with clean water. In case of prolonged irritation medical advice should be sought.

### Fire

Hydroproof Xtra is nonflammable.



## Fosroc Chemicals (India) Pvt. Ltd.

### Head Office

Embassy Point, No. 150,  
2nd Floor, Infantry Road,  
Bangalore 560 001,  
Karnataka

### Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

### telephone

+91 80-42521900

### fax

+91 80-22281510

### e-mail

enquiry.india@fosroc.com

### Regional Offices

#### Chennai

Hills Centre, Old No. 5,  
New No 9, 3rd Cross Street,  
Jeth Nagar, Raja Annamalaipuram,  
Chennai 600 028.  
Ph: 9500064795

#### Mumbai

MBC Park, 12th floor, Office No.12B,  
'D' Block, Near G Corp/Hyper City  
Kasarwadawali, Ghodbunder Road,  
Thane (West) 400 615  
Ph: +91 22 6229 6800

#### Noida

Unit No. 601, Highway Tower-II  
A-13/2, 6th Floor, Sector- 62  
Gautam Buddha Nagar,  
Noida 201 309, Uttar Pradesh  
Ph: +91 120 6121900  
Fax: 0120-4270622

#### Kolkata

304, Jodhpur Park  
Kolkata 700 068  
Ph: +91 33-65343188  
Fax: 033-2499-0278