

Nitobond EP Std

General purpose epoxy bonding agent

Uses

Bonding old and new cementitious substrates.

Advantages

- Can be applied on concrete & mortar substrate
- Facilitates improvement in mechanical strength
- Good positive adhesion
- Can be applied between steel and concrete

Description

Nitobond EP Std is a two component epoxy bonding agent supplied in pre-weighed quantities for ready on-site mixing and use.

Technical support

The company provides a technical advisory source supported by a team of specialists in the field.

Properties

Pot life	Min. 120 minutes @ 35°C
Full hardness	24 hrs
Full cure	7 days
Overlay time	upto 3 hrs
Compressive strength BS 6319 Pt 2	40 N/mm ²
Tensile strength BS 6319 Pt 7	15 N/mm ²
Flexural strength BS 6319 Pt 3	25 N/mm ²
Bond strength ASTM C881	11 N/mm ²

Below 20°C, the times mentioned for potlife and overlay time will increase.

Note: The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary, dependent on actual site conditions.



**GreenPro Ecolabel
Certified by CII**

Application instructions

Preparation

All surfaces to be treated must be sound, dust-free and clean. All laitence should be removed by wire-brushing or any other suitable means. Surfaces contaminated with oil or grease, shall be cleaned thoroughly to remove such contaminants.

Mixing

The entire contents of the hardener can should be poured into the resin container and the two materials thoroughly mixed until a uniform colour is obtained. To facilitate application at temperatures below 10°C the separate components should be warmed in hot water to a maximum of 25°C before mixing.

Coating

Mixed Nitobond EP Std should be brush applied to the prepared substrate. The new concrete should be placed within 3 hours at 35°C to the Nitobond EP Std coated substrate, when it is still in a tacky state.

Cleaning

Tools and equipment shall be cleaned thoroughly after use with Nitoflor Sol.

Estimating

Packaging

Available in 0.5 Litre, 1 Litre and 4 Litre.

Coverage

Actual coverage will depend upon the texture and porosity of the substrates being covered. Typically, 1Litre pack will cover about 2.0-2.5 m² and 4 litre pack around 8.0 - 10.0m² .

Storage

Shelf life

12 months shelf life when stored under normal wear house conditions below 35°C in unopened containers.

Nitobond EP Std

Precautions

Health and Safety

Contact with skin and eyes should be avoided. Gloves should be used when handling these products. If contact with the resin occurs, skin should be washed immediately with strong detergent. A resin removing cream should be used. Eye contamination must be immediately washed with sufficient quantity of water and medical treatment sought.

Fire

Nitobond EP Std is flammable. No naked flame should be allowed near the site. Do not smoke during use.

Additional information

Fosroc manufactures a wide range of products specifically designed for the repair and refurbishment of damaged reinforced concrete. This includes hand-placed and spray grade repair mortars and a comprehensive package of protective coatings. In addition, a wide range of complementary products are available. This includes joint sealants, waterproofing membranes, grouts & anchors and specialised flooring materials.

Separate datasheets are available on these products.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiry.india@fosroc.com

Regional Offices

Chennai

Hills Centre, Old No 5,
New No 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaipuram,
Chennai 600 028.
Ph: 9500064795

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector-62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0278