

PRODUCT DATA SHEET

SikaCeram®-155

Ready to use normal cementitious with no vertical slip tile adhesive for bonding Ceramic Tile.
C1 T classified according to EN 12004

PRODUCT DESCRIPTION

SikaCeram®-155 is a cementitious polymer modified tile adhesive with no vertical slip.

It can create adhesive layers up to 10 mm thickness. It is suitable for Ceramic Tile on Floor and Wall. Indoor and Outdoor.

USES

- Laying all kind of ceramic tiles
- Indoor and outdoor, on walls and floors
- For Absorbing Tile fixing

CHARACTERISTICS / ADVANTAGES

- No vertical slipping
- Application upto 10 mm thick

TESTS

APPROVAL / STANDARDS

One pack normal cement base with no vertical slip adhesive.
Suitable for Ceramic Tiles. EN 12004 Class C1T

PRODUCT DATA

| | |
|-----------------------------|--|
| FORM | Grey Powder |
| PACKAGING | 25 kg bag |
| STORAGE / SHELF LIFE | 12 months from date of production if stored properly in undamaged original sealed packaging, in dry cooled conditions. |

TECHNICAL DATA

| | | | |
|--------------------|---|-------------|--|
| CHEMICAL BASE | Portland cement, selected aggregates, water retention additives and re-dispersible polymer. | | |
| LAYER THICKNESS | 10 mm max | | |
| POT LIFE | ~3-4 hours at 23°C | | |
| OPEN TIME | ~25 minutes at 23°C | (EN 1346) | |
| ADJUSTABILITY TIME | ~35 minutes at 23°C | | |
| CURING DETAILS | Applied product ready for use: | | |
| | Before floor grouting - light foot Traffic | 24-36 hours | |
| | Before wall grouting | 4-6 hours | |

MECHANICAL / PHYSICAL PROPERTIES

| | Value Grey | Requirement EN 12004 | Test Method |
|---|-----------------------|---------------------------------|------------------------|
| Initial Tensile Bond | 1.0 N/mm ² | ≥ 0.5 N/mm ² | EN 1348 |
| Tensile Bond after Heat Action | 0.7 N/mm ² | ≥ 0.5 N/mm ² | EN 1348 |
| Tensile Bond after water immersion | 0.9 N/mm ² | ≥ 0.5 N/mm ² | EN 1348 |
| Slip Resistance | ≤ 0.5 mm | ≤ 0.5 mm | EN 1308 |

CONSUMPTION DOSAGE

The consumption is dependent on the surface profile and roughness of the substrate as well as on the size of the tiles and the application technique (double-spreading, in thin-bed consistency, or single spreading, in flow-bed consistency). As a guide, in kilograms of powder per m² : 1.2 kg / m² /mm of thickness

SUBSTRATE QUALITY

The substrate must be cement laitance free, clean and free from dirt, oil, grease or other contaminants and loose or friable particles. The substrate must be perfectly flat, sound and free from parts easily removed, non-deformable and correctly aged. For builds greater than 10mm thick, use the appropriate Sika MonoTop® or Sika® Level product(s).

SUBSTRATE PREPARATION

SikaCeram-155 is applied directly on plasters and cementitious substrates, cement-lime mortars, concrete, plasterboard, floater finished concrete.

SUBSTRATE TEMPERATURE

+5°C min; +35°C max

AMBIENT TEMPERATURE

+5°C min; +35°C max

APPLICATION INSTRUCTIONS**MIXING RATIO**

~ 6.5 -7 litres of water (26% - 28%) for 25 kg of SikaCeram-155 Grey

MIXING

Mix the contents of a 25 kg bag with the required amount of water (as specified above), using an electric mixer and a suitable mixing spiral at low speed, in a clean bucket. Do not exceed a mixing speed of 500 rpm as doing so may reduce the final strength of the cured product. Mix to obtain a smooth paste free of lumps. After mixing, leave the product for 5-10 minutes, then briefly stir the mixture prior to application. This should result in a very creamy, easily spreadable, and highly thixotropic adhesive.

**APPLICATION METHOD /
TOOLS**

SikaCeram-155 is applied using a notched trowel. The amount of product should be enough to ensure complete wetting of the tile. Tiling has to be carried out on fresh adhesive, exerting an adequate pressure to ensure contact with the adhesive to form a full bond. If a surface film has formed on the adhesive, it is necessary to trowel over the previously applied adhesive layer. Avoid wetting the adhesive already applied with water.

To lay tiles sized 900 cm² (e.g. 30 x 30 cm) or larger, the double-spreading (buttering) thin-bed consistency or single-spreading flow-bed consistency techniques of adhesive application is always recommended.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.

**NOTES ON APPLICATION /
LIMITATIONS**

SikaCeram®-155 shall not be applied in the following cases:

- On metal surfaces and wood

All technical data stated in this Product Data Sheet is based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. Values achieved in laboratory conditions: 23°C ± 2°C – R.H. 50% ± 5%. Higher temperatures reduce the indicated lapse time, oppositely, lower temperatures increase them.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

HEALTH AND SAFETY INFORMATION

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations.

Sika India Pvt. Ltd.
Commercial Complex II
620, Diamond Harbour Road
Kolkata 700034
India

Phone: +91 33 2447 2448 /2449
Telefax: +91 33 2396 8688
Email: info.india@in.sika.com
Website: ind.sika.com